



DATA SHEET NO. 6506-500

VERTIBARRIER NS

Cold-Applied, Moisture-Cured Waterproofing Membrane

DESCRIPTION

VERTIBARRIER NS is a single-component, cold-applied, solvent-free, water-activated, waterproofing system. The product is designed for vertical surfaces, but in certain situations, it can be applied on horizontal surfaces. It does not shrink and has a low volatile organic compound (VOC) content. It will not crack in extreme cold or flow due to softening at high temperatures.

USES

VERTIBARRIER NS is suitable for use on vertical exterior concrete surfaces where protection from water intrusion is desired. The product can be used for both above-grade and below-grade applications. VERTIBARRIER NS is intended for use on foundation walls, concrete tunnels, and planters. VERTIBARRIER NS is also suitable for plaza decks and elevated composite decks and also in between-slab (split-slab) applications. VERTIBARRIER NS is used on concrete, metal, and wood surfaces.

FEATURES/BENEFITS

- Fast curing at 23° C; no dust pick-up.
- May be applied to green concrete.
- Fast cure; speeds production.
- Cured with water addition in as little as two hours/Can be recoated same day for two-coat application.
- Will not harm foam plastic insulations.
- Remains undamaged due to freezing.
- Cures to a tough, flexible membrane.
- Rapid curing/Add 0.95 L (1 qt.) water per 18.9 L (5 gal.) pail

PACKAGING

18.93 Litre (5 Gal.) Pails

COVERAGE

Approximate coverage per 3.78 L (1 gal.)

2.4 m ² (26 ft. ²)	60 mils (dry)
1.6 m ² (17.5 ft. ²)	90 mils (dry)
1.2 m ² (13 ft. ²)	120 mils (dry)

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 21° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS/STANDARDS

- ASTM C836
- Canada VOC Concentration Limits for Architectural Coatings Regulations

TECHNICAL DATA

Property	Typical Test Value	Test Method
Solids Content by Weight, %	93 - 99	ASTM C2369
Solids Content by Volume, %	92 - 98	ASTM D2697
Initial Viscosity @ 23° C	25,000 – 35,000 cps	
Working Time with addition of potable water	20 minutes at 23.9° C and 50% RH	
Initial Cure with the addition of 0.95 L (1 qt.) of potable water to 18.9 L (5 gal.) of VERTIBARRIER NS	2 hours at 23.9° C and 50% RH	
Hydrostatic Pressure Resistance @ 60 mils	0.68 MPa (100 psi) 70.38 m (231') of water	ASTM D5385
Tear Resistance, Die C	100 PLI (17.5 kN/m)	ASTM D624
Tensile Strength, psi	350	ASTM D412
Elongation at Break, %	550	ASTM D412
Permeability (60 mils) perms	1.15	ASTM E96 B
Permeability (90 mils) perms	0.77	ASTM E96 B
Permeability (120 mils) perms	0.58	ASTM E96 B
Shore A Hardness	25	ASTM D2240
Shore 00 Hardness	Avg. 90	ASTM D2240
Service Temperature, ° F (° C)	-25° - 150° (-31.7° - 65°)	
Minimum Application Temperature, ° F (° C)	Above 30° (-1°) and rising	
VOC Content, g/L	<50	ASTM D2369

APPLICATION

New Concrete Design Finish ... Wet curing is recommended. All membrane curing compounds must be mechanically removed. New concrete should be power washed or blown clean with oil-free compressed air before coating application to ensure removal of dirt or debris that may compromise bond of VERTIBARRIER NS. A test application is always recommended before proceeding with primary application.

Continued Over ...

W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB

www.wrm Meadows.com

info@wrmeadows.com

Surface Preparation ... Concrete must be in sound repair and free of all contaminates, including oil, grease, dust, laitance, and other bond-breaking materials. Concrete should exhibit a concrete surface profile (CSP) of 3 or greater in accordance with the International Concrete Repair Institute (ICRI).

All new and existing concrete substrates to receive VERTIBARRIER NS should be properly prepared and yield a CSP 3 – CSP 5. For existing concrete remedial work or new concrete lacking profile, lightly roughen or rough grind substrate in accordance with ICRI guidelines. A small-scale mockup of the VERTIBARRIER NS system prior to full scale application may occur per project requirements for all interested parties.

All surfaces must be thoroughly dry, not damp, and have no standing water to ensure optimum performance of the VERTIBARRIER NS system.

For metal surfaces, remove all oils or other contaminates on the surface prior to application of VERTIBARRIER NS. Mechanically abrade and solvent wipe to remove any contaminates. Allow the solvent to evaporate completely prior to application of VERTIBARRIER NS.

Joints, Cracks, and Flashing ... Between 1/16" (1.58 mm) and 1/8" (3.2 mm) width must be filled with VERTIBARRIER NS or BEM from W. R. MEADOWS and tooled smooth. Non-moving cracks greater than 1/8" (1.58 mm) should be routed and filled with MEADOW-CRETE GPS from W. R. MEADOWS or comparable structural repair mortar. Once cured, a 60-mil application of VERTIBARRIER NS should be applied over and extending 152.4 mm (6") beyond the patched area. A strip of REINFORCING FABRIC HCR from W. R. MEADOWS should then be brushed onto the membrane while still wet, showing full engagement with the membrane with no wrinkles.

Priming and Decreasing Blistering ... For porous substrates and where air and moisture release may cause pinholes or blistering problems, priming the substrate prior to application of VERTIBARRIER NS is recommended. Discovery of these conditions is generally revealed in the mockup.

Additionally, application of VERTIBARRIER NS during cooling hours of the day or not in direct sunlight may potentially decrease the probability of blistering due to outgassing from the concrete. Do not apply when the surface temperature of the substrate is greater than 43° C.

Mixing ... This is a water-activated waterproofing compound; as such, water is required for proper curing. The waterproofing membrane should be properly mixed with water to achieve optimal performance. Add up to 0.95 L (1 qt.) of potable water per 18.9 L (5 gal. pail of VERTIBARRIER NS.

VERTIBARRIER NS should be thoroughly mixed before adding water. Add up to 0.95 L (1 qt.) of potable water per 18.9 L (5 gal.) pail of VERTIBARRIER NS and mix thoroughly for three minutes using a mechanical mixer at slow speed to ensure a homogeneous texture. Use a mixing blade designed for paints or coatings. Do not use mud or mortar mixers. Take care not to trap air into the material as this will result in blisters in the cured film. Avoid mixing in an up-and-down motion. To decrease the incorporation of air during mixing, the following mixers are recommended:

- Mixer - Collomix® Paddle Mixer Xo 55 R Duo Heavy-duty Forced-action Mixer or similar
- Blade Type – Collomix® Heavy Duty 3-Blade MK-140 HF paddle or Universal WK 120 HF Paddle or similar.

Application Method ... Store VERTIBARRIER NS at 23.9° C at least 12 hours prior to use for ease of application.

VERTIBARRIER NS is applied by roller or trowel in a single coat application of 60 mils. Cure time will vary depending on temperature and humidity. VERTIBARRIER NS has an open working time of 20 minutes at 23.9° C with the addition of potable water. Make sure all application of the membrane has been completed within this timeframe.

At 23.9° C and 50% relative humidity, allow coating to cure a minimum of 2 - 4 hours before proceeding to subsequent coats, but no more than eight hours apart. As ambient, substrate, and material temperatures increase, an oily-like film may develop on the surface and act as a bond breaker. For next-day or second-coat applications, rub the areas to be overlapped down [152 - 203 mm wide (6" - 8")] with acetone, mineral spirits, or xylene. This removes the oil film. Do not use alcohol.

Recoat times will vary depending on temperature, direct sun exposure and humidity. The higher the temperature and humidity, the faster the cure. Applications exposed to direct sun heating will also cure faster. Typically, if more than 48 hours pass between coats, the surface must be solvent wipe and primed. (Refer to VERTIBARRIER PRIMING GUIDE). Due to project conditions and temperature, the recoat window of application may be decreased, requiring priming as little as 24 hours.

Membrane Protection Course ... Protect VERTIBARRIER NS with MEL-DRAIN™ (type with the polymeric backing film) from W. R. MEADOWS or alternatively PERMINATOR® 10 or 15 mil from W. R. MEADOWS.

VERTIBARRIER NS will not typically wash off if rain begins during or after application. Stop all work if rain begins and protect open or unused material from rainfall.

Cleanup ... Uncured VERTIBARRIER NS cleans up easily with alcohol. Cured material is best removed by mechanical means.

® SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.

PRECAUTIONS

Do not expose product to exterior UV for longer than 14 days. VERTIBARRIER NS is not to be used as a liner in a water-containing structure and is not to be used as an exposed or wearing surface. For this purpose, use the GEMITE® line of products. VERTIBARRIER NS is not compatible with asphalt, polymeric-based products, or asphaltic membranes. Do not use on surfaces that are later to be painted. It cannot withstand direct wear or abrasion. Containers that have been opened must be used as soon as possible. Do not dilute product with solvent under any circumstance. VERTIBARRIER NS is not recommended for use over magnesite, gypsum, lightweight concrete, or where chained or studded tires may be used. Concrete must exhibit 20.7 MPa (3000 psi) minimum strength prior to application of VERTIBARRIER NS. Always install a mockup prior to full installations.

This data sheet provides a summary of the factors, precautions, limitations, and design theories that should be considered when designing a complete waterproofing and drainage system, but is not standalone or complete; project, environmental, and application specific requirements must be considered before drafting a guide specification, determining suitability, or application of material. Project suitability of the VERTIBARRIER NS is the sole responsibility of the licensed design professional or installing contractor.

Refer to safety data sheet for health and safety information.
WARNING: This product contains isocyanates.

MASTERFORMAT NUMBER AND TITLE

07 14 16 - Cold Fluid-Applied Waterproofing

01/06/25



® SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.