



DATA SHEET NO. 7200-121

AIR-SHIELD™

Self-Adhering Air/Vapour and Liquid Moisture Barrier

DESCRIPTION

AIR-SHIELD self-adhering air/vapour and liquid moisture barrier is part of a total W. R. MEADOWS system to complete the building envelope. It is a rubberized asphalt, roll-type product that is nominally 40 mils thick. The membrane's controlled thickness is fabricated from cross-laminated polyethylene bonded to specially modified asphalt.

This unique, self-adhesive membrane, protected by a special release paper, is strong and durable. It remains flexible when surface mounted and will adhere to most primed surfaces at minimum temperatures of 4°C (40°F). The membrane provides excellent protection as a tough barrier or flashing that won't shrink, sag, dry out, crack, or rot. It offers excellent resistance to punctures during installation. The self-healing characteristics of AIR-SHIELD facilitate recovery if minimal damage is sustained under normal use applications, i.e. when penetrated with self-tapping screws or nails.

PACKAGING

AIR-SHIELD is packaged in rolls of 0.97 m x 22.86 m (38.5" x 75'). AIR-SHIELD can also be cut to desired width.

Optional sizes include 10.1 cm (4"), 15.2 cm (6"), 22.8 cm (9"), 30.5 cm (12"), 40.6 cm (16"), 45.7 cm (18"), 50.8 cm (20"), and 61 cm (24"), all 22.86 m (75') long.

STORAGE

AIR-SHIELD should be stored palletized and protected from rain and/or physical damage. Do not store at temperatures above 32.2°C (90°F) for extended periods of time. Do not leave membrane exposed to direct sunlight. Do not double-deck pallets. Store away from sparks or flames. Outdoors, store AIR-SHIELD on pallets and completely cover.

USES

AIR-SHIELD self-adhering air/vapour barrier and liquid moisture barrier is designed for a variety of uses.

Primary applications include cavity wall and masonry wall construction. AIR-SHIELD works equally well as an air and/or vapour barrier on precast concrete, cast-in-place concrete, masonry (concrete block), interior and exterior gypsum board. Styrofoam, primed steel, aluminum mill finish, anodized aluminum, primed galvanized metal, drywall and plywood.

SPECIFICATIONS/STANDARDS

- Meets CAN/CGSB-51-33, Type I Water Vapour Permeance Requirements
- 2020 National Building Code of Canada
- ABAA Section 07261 Self-Adhering Air and Vapour Barrier Specification

MAINTAIN ENERGY EFFICIENCY

AIR-SHIELD provides an effective barrier to air exfiltration and infiltration, reducing condensation within the wall assembly, and increasing efficiency of a building's mechanical system. Wet insulating materials lose much of their R-factor performance characteristics, reducing the energy efficiency of the structure. W. R. MEADOWS thermal and moisture protection products play a key role in *maintaining* the structure's energy efficiency and aiding in the integrity of other structural systems, such as insulation.

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrm Meadows.com
info@wrmeadows.com

TECHNICAL DATA	
TEST	RESULTS
Colour	White
Thickness	40 mils (1 mm)
Pliability @ -32° C (-25° F)	No effect
Tensile Strength Film	
ASTM D 412 modified (MD)	27.6 MPa (4,000 psi)
ASTM D 882 (MD)	4.1 N/mm (23.5 lb./in.)
Elongation Film	
ASTM D 412 modified (MD, %)	400 (Typical)
ASTM D 882 (MD, %)	400 Min.
Puncture Resistance	
ASTM E 154	178 N (40 lbf) Min.
Water Vapour Permeance (free film)	
ASTM E-96, Procedure B	0.035 Perms
Water Absorption (% by weight)	
ASTM D 1970	0.25 Max.
ASTM D 570-81	0.1 Max.
Water Penetration: ASTM E331	Pass
*Application Temperature	4° C (40° F) Min.
Low Temperature Flexibility @ -30° C (-22° F) (CGSB 37-GP-56m)	PASS
Service Temperature	-40° C - 70° C (-40° F - 158° F)
Lap Peel Strength @ 4° C (39° F) (ASTM D 903, 180° Bend)	1.75 N/mm (10 lbf/in) width

Air Leakage tested per ASTM E 283, ASTM E 2178-01, and ASTM E 2357

Pressure		Air Leakage (National Building Code of Canada Requirement)	Results for AIR-SHIELD	Air Leakage (National Building Code of Canada Requirement)	Results for AIR-SHIELD
Pa	lb./ft. ²	L/S/m ²		cfm/ft. ²	
75	1.57	0.02	Less than 0.02	0.004	Less than 0.004

** Independent tests, available upon request

APPLICATION

Surface Preparation ... All surfaces to be protected must be clean, dry, frost-free, and smooth. Remove any sharp protrusions and repair all defects. All surfaces to receive AIR-SHIELD must be clean of oil, dust, and excess mortar. Strike masonry joints flush. Concrete surfaces must be smooth and without large voids, spalled areas, or sharp protrusions. Concrete must be cured a minimum of 14 days and must be dry before AIR-SHIELD is applied. Where curing compounds are used, they must be clear resin-based, without oil, wax or pigments. Prepare substrate per manufacturer's instruction prior to application of membrane.

FEATURES/BENEFITS

- Low permeability – prevents the transmission of air and inhibits moisture vapour through porous building materials.
- Provides a complete above-grade air, vapour, and water barrier on a variety of construction materials.
- Controlled thickness membrane is ideal for air barrier applications.
- Cross-laminated polyethylene film has excellent tensile strength, elongation, and tear resistance.
- Modified membrane is flexible at low temperatures.
- Excellent adhesion to prepared substrates of pre-cast concrete, cast-in-place concrete, masonry (concrete block), interior and exterior gypsum board, Styrofoam, primed steel, aluminum mill finish, anodized aluminum, primed galvanized metal, drywall, and plywood.
- Self-gasketing around fasteners; for more information, see TECHNICAL BULLETIN: FASTENER PENETRATION THROUGH AIR-SHIELD MEMBRANES.
- No flame required.
- Low temperature version also available – can be applied at temperatures between -7° C (20° F) and 16° C (60° F)
- AIR-SHIELD XLT can be applied at minimum temperatures of -18° C (0° F).

All surfaces to which AIR-SHIELD is to be applied must be addressed with either MEL-PRIME™ or MEL-PRIME W/B adhesive from W. R. MEADOWS. MEL-PRIME may be applied to an area that is to be covered the same day. Uncovered areas must be re-addressed the next day. See container for complete application directions, drying information, and precautions.

® SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.

Application Method ... AIR-SHIELD self-adhesive air/vapour and liquid moisture barrier can be applied at minimum temperatures of 4° C (40° F). Apply membrane to surface addressed with MEL-PRIME by removing release paper and rolling membrane firmly into place. Remove release paper only as membrane is being applied. Ensure membrane is fully adhered and remove all wrinkles and/or fish mouths. Cut AIR-SHIELD membrane with a utility knife to detail around protrusions and masonry reinforcing. Seal all end laps and protrusions with POINTING MASTIC from W. R. MEADOWS. Overlap subsequent courses of membrane a minimum of 50.8 mm (2"). Vertical terminations of AIR-SHIELD should either be tied into the wall system or mechanically fastened with TERMINATION BAR from W. R. MEADOWS. AIR-SHIELD is not designed for permanent exposure. Good construction practices call for application of insulation as soon as possible to protect the air barrier.

When used as a flexible wall flashing, AIR-SHIELD should be recessed 13 mm (1/2") from the face of the masonry. Flashing should not be permanently exposed to sunlight. Do not allow the rubberized asphalt surface of the flashing membrane to come in contact with sealants containing solvents, creosote, uncured coal tar products, EPDM, or PVC components.

Cleanup ... Tools, etc. can be cleaned with mineral spirits, paint thinner or aromatic solvent.

COVERAGE

Coverage is approximately 22.3 m² (240 ft.²). Net coverage when lapped 50 mm (2") is 21.1 m² (228 ft.²).

SAFETY & TOXICITY

No adverse effects expected with normal product use. Cotton work gloves and safety goggles are recommended. Refer to Material Safety Data Sheet for complete health and safety information.

ACCESSORIES

MEL-PRIME W/B ... This water-based adhesive prepares surfaces for AIR-SHIELD membrane application. Product is ready to use and requires no additional mixing. MEL-PRIME W/B emits no unpleasant odours and works with all waterproofing membranes from W. R. MEADOWS. Can be applied easily by manual spraying or with a roller. VOC-compliant. MEL-PRIME W/B is ideal for use at temperatures of 4° C (40° F) and above.

Coverage: 6.14 - 8.6 m²/L (250 - 350 ft.²/U.S. gallon)

Packaging: 3.79 Litre (1 U.S. Gallon) Units, 4/Carton and 18.93 Litre (5 U.S. gallon) Pails

MEL-PRIME ... This solvent-based adhesive can be used at temperatures below 4° C (40° F) and above. Can be applied with a roller or brush.

Coverage: 6.14 - 7.4 m²/L (250 - 300 ft.²/U.S. gallon)

Packaging: 3.79 Litre (1 U.S. gallon) Cans and 18.93 Litre (5 U.S. Gallon) Pails

TERMINATION BAR ... As an option, TERMINATION BAR may be used to mechanically fasten the membrane.

Packaging: (25) x 10' (3.05 m) pieces per 20 lb. carton (250 lineal ft.)

POINTING MASTIC ... Used for sealing exterior vertical and horizontal terminations, laps, around protrusions, and top edges of TERMINATION BAR.

Coverage: Approximately 61 metres (200 lineal feet) per 3.79 litres (1 U.S. gallon) when used as directed.

Packaging: 18.93 Litre (5 U.S. gallon) Pails or 857.65 mL (29 oz.) cartridges, 12/carton.

MASTERFORMAT NUMBER AND TITLE
07 27 13 - Modified Bituminous Sheet Air Barriers

2025-07-22

